



	测试方法	测试条件	单位	DG-407	<b>DG-417</b>	DG-427	DG-437	DG-MG29	DG-MG94	DG-FR11	DG-FR15
I ZOD	IS0180	4.0mm, 23℃	kJ/m <sup>2</sup>	24.5	<b>19.7</b>	18.5	12.6	33.5	16.9	12.6	18.1
	IS01133	220℃, 10kg	g/10min	17.0	<b>19.1</b>	26.7	18.6	9.2	35.5	19.6	15.1
	IS0178	4.0mm, 2.0mm/min	Mpa	2210	<b>2287</b>	2229	2598	1845	2365	2449	2191
	IS0178	4.0mm, 2.0mm/min	Mpa	67.2	<b>70.2</b>	67.7	78.9	54.6	69.5	71.8	64.7
	IS0527	4.0mm, 50mm/min	Mpa	45.5	<b>46.4</b>	45.5	51.5	39.4	43.7	47.5	40.5
	IS0306	50N, 50℃/h, (3-6.5) mm	℃	98.9	<b>99.5</b>	99.1	100.2	98.2	99.1	84.2	83.6
	IS01183	23℃	g/cm <sup>3</sup>	1.04	<b>1.04</b>	1.04	1.04	1.04	1.04	1.16	1.16
	GB/T9342	-	R Scale	111	<b>111</b>	111	110	102	112	104	104
	IS075	-	℃	75	<b>75</b>	75	76	72	76	65	63
	UL-94	1.5mm	-	HB	<b>HB</b>	HB	HB	HB	HB	V-0	V-0