



| | 测试方法 | 测试条件 | 单位 | DG-407 | DG-417 | DG-427 | DG-437 | DG-MG29 | DG-MG94 | DG-FR11 | DG-FR15 |
|-------|-------------|---------------------------|---------|--------|--------|--------|---------------|---------|---------|---------|---------|
| I ZOD | ASTM D-256 | 3.2mm, 23℃ | J/m | 248 | 208 | 190 | 160 | 342 | 183 | 121 | 184 |
| | ASTM D-1238 | 220℃×10kg | g/10min | 17.0 | 19.5 | 26.7 | 18.1 | 8.6 | 34.5 | 21.7 | 15.1 |
| | ASTM D-790 | 3.2mm, 2.0mm/min | Mpa | 2166 | 2230 | 2188 | 2438 | 1793 | 2215 | 2390 | 2125 |
| | ASTM D-790 | 3.2mm, 2.0mm/min | Mpa | 63.2 | 64.9 | 63.7 | 70.8 | 51.8 | 62.6 | 67.3 | 60.1 |
| | ASTM D-638 | 3.2mm, 50mm/min | Mpa | 45.9 | 47.3 | 45.8 | 51.4 | 40.2 | 43.6 | 47.8 | 40.2 |
| | ASTM D-1525 | 50N, 50℃/h, (3-6.5) mm | ℃ | 98.9 | 99.5 | 99.1 | 100.3 | 97.8 | 97.6 | 85.2 | 83.6 |
| | ASTM D-792 | 23/23℃ | - | 1.04 | 1.04 | 1.04 | 1.04 | 1.04 | 1.04 | 1.16 | 1.16 |
| | ASTM D-785 | - | R Scale | 111 | 111 | 111 | 110 | 102 | 112 | 104 | 104 |
| | ASTM D-648 | - | ℃ | 75 | 75 | 75 | 76 | 72 | 76 | 65 | 63 |
| | UL-94 | 1.5mm | - | HB | HB | HB | HB | HB | HB | V-0 | V-0 |