



	测试方法	测试条件	单位	DG-407	DG-417	DG-427	DG-437	DG-MG29	DG-MG94	DG-FR11	DG-FR15
I ZOD	ASTM D-256	3.2mm, 23℃	J/m	248	208	190	160	342	183	121	<b>184</b>
	ASTM D-1238	220℃×10kg	g/10min	17.0	19.5	26.7	18.1	8.6	34.5	21.7	<b>15.1</b>
	ASTM D-790	3.2mm, 2.0mm/min	Mpa	2166	2230	2188	2438	1793	2215	2390	<b>2125</b>
	ASTM D-790	3.2mm, 2.0mm/min	Mpa	63.2	64.9	63.7	70.8	51.8	62.6	67.3	<b>60.1</b>
	ASTM D-638	3.2mm, 50mm/min	Mpa	45.9	47.3	45.8	51.4	40.2	43.6	47.8	<b>40.2</b>
	ASTM D-1525	50N, 50℃/h, (3-6.5) mm	℃	98.9	99.5	99.1	100.3	97.8	97.6	85.2	<b>83.6</b>
	ASTM D-792	23/23℃	-	1.04	1.04	1.04	1.04	1.04	1.04	1.16	<b>1.16</b>
	ASTM D-785	-	R Scale	111	111	111	110	102	112	104	<b>104</b>
	ASTM D-648	-	℃	75	75	75	76	72	76	65	<b>63</b>
	UL-94	1.5mm	-	HB	HB	HB	HB	HB	HB	V-0	<b>V-0</b>