



	测试方法	测试条件	单位	DG-407	DG-417	DG-427	DG-437	<b>DG-MG29</b>	DG-MG94	DG-FR11	DG-FR15
I ZOD	IS0180	4.0mm, 23℃	kJ/m <sup>2</sup>	24.5	19.7	18.5	12.6	<b>33.5</b>	16.9	12.6	18.1
	IS01133	220℃, 10kg	g/10min	17.0	19.1	26.7	18.6	<b>9.2</b>	35.5	19.6	15.1
	IS0178	4.0mm, 2.0mm/min	Mpa	2210	2287	2229	2598	<b>1845</b>	2365	2449	2191
	IS0178	4.0mm, 2.0mm/min	Mpa	67.2	70.2	67.7	78.9	<b>54.6</b>	69.5	71.8	64.7
	IS0527	4.0mm, 50mm/min	Mpa	45.5	46.4	45.5	51.5	<b>39.4</b>	43.7	47.5	40.5
	IS0306	50N, 50℃/h, (3-6.5) mm	℃	98.9	99.5	99.1	100.2	<b>98.2</b>	99.1	84.2	83.6
	IS01183	23℃	g/cm <sup>3</sup>	1.04	1.04	1.04	1.04	<b>1.04</b>	1.04	1.16	1.16
	GB/T9342	-	R Scale	111	111	111	110	<b>102</b>	112	104	104
	IS075	-	℃	75	75	75	76	<b>72</b>	76	65	63
	UL-94	1.5mm	-	HB	HB	HB	HB	<b>HB</b>	HB	V-0	V-0